

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **2002173899 A**(43) Date of publication of application: **21.06.02**

(51) Int. Cl. **D21H 27/20**
D21H 13/24
D21H 15/04
D21H 27/00
D21H 27/30

(21) Application number: **2001312009**(22) Date of filing: **04.09.01**(30) Priority: **07.09.00 JP 2000312647**(71) Applicant: **YOSHIKAWA KAMI SHOJI KK**

(72) Inventor:
SUZUKI KUNIO
KASUGATA SATOSHI
SUMI SEIICHI
UMEMURA MASAHIRO
KITAJIMA NAOTAKE

(54) **NONWOVEN FABRIC FOR WALL PAPER**
SUBJECTED TO PAPERMAKING PROCESS AND
METHOD FOR PRODUCING THE NONWOVEN
FABRIC AND THE RESULTANT NONWOVEN
FABRIC WALL PAPER.

the above nonwoven fabric is characterized by having an emboss depth of 0.10-0.50 mm and a surface abrasive strength rated at a rank of 5.0.

COPYRIGHT: (C)2002,JPO

(57) Abstract

PROBLEM TO BE SOLVED: To provide a nonwoven fabric wall paper solving the problems of difficulty in combining three-dimensional feeling or voluminous feeling, increased surface abrasive strength and aesthetic surface printing together and of difficulty in producing such a wall paper at low cost in addition to accomplishing the above combination in conventional nonwoven fabric wall paper.

SOLUTION: This nonwoven fabric for wall paper is composed of a layer containing 25-60 wt.% of thermofusible fibers and a 2nd layer containing 35-75 wt.% of the thermofusible fibers; wherein the content of the thermofusible fibers in the 2nd layer is ≤ 10 wt.% higher than that in the 1st layer, both the layers are produced by an integrated wet papermaking process, and the surface abrasive strength of the 2nd layer is rated at a rank of ≤ 3.5 . The 2nd objective method for producing the above nonwoven fabric is also provided. The other objective nonwoven fabric wall paper made of

